

Corax N234 (ISAF - HS)

Carbon black for Rubber - Corax Hard Grade



1. N220 , MODULUS,
2. Low Structure Incorporation Time 가
Dispersion Time ()



	(mg/g)	: 119
	(m ² /g)	: 126
	(% vs IRB#3)	: 123
DBP	(cc/100g) DBP	: 125
	(% Max.)	: 0.75
가	(% Max.)	: 1.0
		: 7.0
	(kg/m ³)	: 335
#325	(ppm, Max.)	: 300
#35	(ppm, Max.)	: 0



Tire Tread

